Technical data sheet

Chemicals



PP REPSOL ISPLEN PP080G2M

REPSOL ISPLEN PP080G2M is a homopolymer grade with a high fluidity intended for injection moulding. It is characterised by good flow properties that enables to fill the mould easier and by short cycle times with big articles. Articles manufactured with this grade have excellent chemical resistance, are easily decorated and can accept different colouring systems.

Applications

REPSOL ISPLEN PP080G2M is widely used for the production of consumer goods such us:

- Food containers and rigid packaging.
- Vacuum and cosmetic flasks.
- Garden and domestic furniture
- Base product for compounds

Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	MÉTHOD
General			
Melt flow rate (230°C/ 2,16 kg)	20	g/10 min	ISO 1133
Density at 23°C	905	kg/m ³	ISO 1183
Mechanical Flexural modulus of elasticity Charpy impact strength (23°C,notched)	1.600 3	MPa kJ/m²	ISO 178 ISO 179
Thermal HDT 0,45 MPa	85	٥C	ISO 75
Others			

 Shore Hardness
 70
 ISO 868

 REPSOL ISPLEN PP080G2M complies with the European Directives regarding materials intended for contact with foodstuffs. The product mentioned herein is not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

Storage

REPSOL ISPLEN PP080G2M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

January 2017

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed. Technical Service and Development: Repsol Technology Centre Ctra. de Extremadura AS, Km 18 28931 Móstoles. Madrid Tel. +34 91 753 86 00 atd_poliolefinas@repsol.com Headquarters: Méndez Álvaro, 44 28045 Madrid Spain www.chemicals.repsol.com Customer Care: sacrq@repsol.com